

HempBlock Mortar

MORTAR SPECIALLY DESIGNED FOR MASONRY OF
HEMPBLOCK Veneer series 100,150,200,300

INFORMATIONS PRATIQUES :

- Specifics :
- Sold in 25 kg bags
- CE certified
- Standard: EN 998.2
- Type: G
- Conservation & Guarantee:
- - 1 year from date of manufacture, protected from moisture and in original, unopened packaging.
- Manufacturer's standard liability
- Climatic precautions:
- - Use between 5 ° C and 30 ° C
- Additional data
- - Water retention > 90%
- - Setting start time:
- > 3 hours
- Irritating product; use PPA

Ready-to-mix hydraulic lime mortar, combining the ease and safety of ready-mixed mortar with the flexibility and durability qualities of traditional lime mortars.

PREPARATION OF THE ADHESIVE MORTAR

- Mix a bag of M.B.M. with 3.5 to 4 liters of water per bag.
- The mortar can be made either with a concrete mixer or using a portable stick mixer (slow speed).
- Mixing time ; 3 to 5 minutes.

CONSUMPTION AND RENDEMENT

	Quantity / m ² of blocks traditionally layed	Quantity / m ² of bricks laid with a notched trowel
HempBLOCK 100	7 kg / m ²	3,5 kg / m ²
HempBLOCK 150	10,5 kg / m ²	5,5 kg / m ²
HempBLOCK 200	14 kg / m ²	7 kg / m ²
HempBLOCK 300	21 kg / m ²	11 kg / m ²